



REZKLAD® HP GROUT C

DESCRIPTION

REZKLAD HP GROUT C is a carbon filled, high performance, acid, caustic and solvent resistant grout for quarry tile and brick paver floor systems installed by the Tilesetter's method.

TYPICAL USES

REZKLAD HP GROUT C is recommended for the food processing, beverage, pharmaceutical and electronic industries that require long term performance of floors exposed to chemicals, mechanical abuse and rolling traffic.

REZKLAD HP GROUT C is certifiable for use in USDA inspected facilities. It also offers resistance to hot water and steam wash downs and will not support the growth of bacteria.

REZKLAD HP GROUT C is also an excellent product for re-grouting existing brick and tile floor joints that have eroded. The high bond strength feature provides maximum adhesion to shallow joints. The low odor of the grout permits re-grouting in plants without special ventilation. The water washing feature of REZKLAD HP GROUT C eliminates the need for special masking or waxing of the brick or tile to prevent staining.

CHEMICAL RESISTANCE

REZKLAD HP GROUT C is resistant to dilute organic acids, alkalies, such as sodium hydroxide and potassium hydroxide, and organic solvents. It is also resistant to hydrochloric acid, phosphoric acid, hydrofluoric acid, 93% sulfuric acid, 30% nitric acid and 30% chromic acid as well as toluene, xylene and benzene. Refer to the chemical resistance chart for specific information. REZKLAD HP GROUT C complies with specifications of ASTM C658 and ANSI A118.3.

METHOD OF INSTALLATION

REZKLAD HP GROUT C is designed to be installed by the Tilesetter's method. The quarry tile or brick pavers are set in a bond coat of REZKLAD HP GROUT C or RED FURNANE® SETTING BED, Data Sheet 5-55PI, with a nominal 1/4" space between the masonry units. After the bond coat has set, the REZKLAD HP GROUT C is floated into the joints.

AVAILABLE COLORS

REZKLAD HP GROUT C is available in black only.

PHYSICAL PROPERTIES

| PROPERTY | TEST METHOD | TYPICAL VALUE |
|---|-------------|---|
| Density | ASTM C905 | 79 lb./cu. ft. (1.26 g./cc.) |
| Bond Strength, 7 days @ 77°F (25°C) | ASTM C321 | Brick fails |
| Tensile Strength, 7 days @ 77°F (25°C) | ASTM C307 | 1,500 psi. (10.3 MPa) |
| Compressive Strength, 7 days @ 77°F (25°C) | ASTM C579 | 11,200 psi. (77.2 MPa) |
| Flexural Strength, 7 days @ 77°F (25°C) | ASTM C580 | 3,160 psi. (21.8 MPa) |
| Coefficient of Thermal Exp., in./in./°F (cm./cm./°C) | ASTM C531 | 3.2 x 10 ⁻⁵ (5.8 x 10 ⁻⁵) |
| Linear Shrinkage | ASTM C531 | < 0.2 % |
| Water Absorption | ASTM C413 | < 0.3 % |
| Initial Set | ANSI A118.3 | > 2 hours |
| Temperature Resistance Continual Intermittent | | 185°F (85°C) 212°F (100°C) |

PACKAGING - REZKLAD HP GROUT C

6 lb. 12 oz. (3.1 kg.) Unit Consisting of:

- One - 1-qt. can of Rezklad HP Grout Resin
(1 lb. 8 oz. [680 g.]
- One - 1-pt. can of Rezklad HP Grout Hardener
(12 oz. [340 g.]
- One - bag of Rezklad HP Grout Carbon Powder
(4 lb. 8 oz. [2.0 kg.]
- Nylon Scrub Pad, Rubber Gloves

21 lb. 6 oz. (9.7 kg.) Unit Consisting of:

- One - 1/2-gal. can of Rezklad HP Grout Resin
(4 lb. 12 oz. [2.2 kg.]
- One - 1/2-gal. can of Rezklad HP Grout Hardener
(2 lb. 6 oz. [1.1 kg.]
- One - bag of Rezklad HP Grout Carbon Powder
(14 lb. 4 oz. [6.5 kg.]
- Nylon Scrub Pad, Rubber Gloves

214 lb. 8 oz. (97.3 kg.) Unit Consisting of:

- One - 5-gal. pail of Rezklad HP Grout Resin
(48 lb. [21.8 kg.]
- One - 5-gal. pail of Rezklad HP Grout Hardener
(24 lb. [10.9 kg.]
- Five - bags of Rezklad HP Grout Carbon Powder
(28 lb. 8 oz. [12.9 kg.]) ea.
- Nylon Scrub Pad, Rubber Gloves

ESTIMATING TABLES - REZKLAD HP GROUT C

FLOOR AREA

| Brick Size | 1/4" Wide x Full Depth Joint Square Feet per Unit | | |
|-----------------------|--|-------------------|--------------------|
| | 6 lb. 12 oz. Unit | 21 lb. 6 oz. Unit | 214 lb. 8 oz. Unit |
| 6" x 6" x 1/2" | 26 sq. ft. | 82 sq. ft. | 831 sq. ft. |
| 6" x 6" x 3/4" | 17 sq. ft. | 55 sq. ft. | 544 sq. ft. |
| 8" x 3-7/8" x 1" | 11 sq. ft. | 36 sq. ft. | 365 sq. ft. |
| 8" x 3-7/8" x 1-3/16" | 9 sq. ft. | 30 sq. ft. | 308 sq. ft. |
| 8" x 3-7/8" x 1-3/8" | 8 sq. ft. | 26 sq. ft. | 266 sq. ft. |
| 8" x 4" x 1/2" | 23 sq. ft. | 74 sq. ft. | 746 sq. ft. |
| 8" x 4" x 1-3/8" | 8 sq. ft. | 27 sq. ft. | 271 sq. ft. |
| 8" x 4" x 1-1/2" | 7 sq. ft. | 24 sq. ft. | 248 sq. ft. |

COVE BASE

REZKLAD HP GROUT C may be used for the cove base joints. Maximum joint width for these applications is 1/4" (6.4 mm.). Add approximately 20% additional powder by weight to standard grout mix to achieve mortar consistency.

| Cove Size | 1/4" Wide x Full Depth Joint Linear Feet per Unit | | |
|--------------------------|--|-------------------|--------------------|
| | 6 lb. 12 oz. Unit | 21 lb. 6 oz. Unit | 214 lb. 8 oz. Unit |
| 5" H x 6" L x 1/2" | 52 lin. ft. | 166 lin. ft. | 1,668 lin. ft. |
| 5" H x 6" L x 3/4" | 34 lin. ft. | 110 lin. ft. | 1,112 lin. ft. |
| 5" H x 8" L x 1-3/16" | 19 lin. ft. | 60 lin. ft. | 610 lin. ft. |
| 5" H x 8" L x 1-3/8" | 16 lin. ft. | 52 lin. ft. | 527 lin. ft. |
| 3-7/8" H x 8" L x 1-3/8" | 23 lin. ft. | 74 lin. ft. | 750 lin. ft. |

Bond Coat @ 3/32" 10 ft² per 6 lb. 12 oz. unit 34 ft² per 21 lb. 6 oz. unit 347 ft² per 214 lb. 8 oz. unit
 Bond Coat @ 1/8" 8 ft² per 6 lb. 12 oz. unit 25 ft² per 21 lb. 6 oz. unit 260 ft² per 214 lb. 8 oz. unit

Material estimating quantities may vary depending on job conditions and application techniques. Material quantities above are theoretical and don't include a safety factor. Above estimating is based on a weight ratio of 100 parts resin to 50 parts hardener to 300 parts powder. Decreasing the powder component to 270 parts will decrease the estimated coverage by approximately 6%; decreasing the powder component to 240 parts will decrease the estimated coverage by approximately 10%.

TEMPERATURE DURING APPLICATION

Store REZKLAD HP GROUT C at 70°F (21°C) to 80°F (27°C) for 24 hours prior to use. The best working characteristics of the grout will be attained when the temperature of the substrate, air and REZKLAD HP GROUT C are between 60°F (16°C) and 85°F (29°C).

Minimum temperature for installation is 45°F (7°C). At temperatures below 45°F (7°C), the product may not set or cure properly.

MEASURING OF THE REZKLAD HP GROUT C COMPONENTS

In the absence of a scale to weigh the components, approximate volume measurements are provided. Select a clean, dry, plastic or metal container equal to or larger than the desired component volume. Using a graduated measuring cup, measure and pour the prescribed fluid ounces (liters) of water into the container. Mark the fluid level. Remove the water and dry the container. At the fluid level mark, insert a self tapping sheet metal screw through the side wall of the container. Clearly mark the container for the intended use resin, hardener or powder and the volume measurement.

Powder component: Loosely pour the powder to the fluid level mark. Do not shake the powder container to settle powder. Powder volumes listed on the Data Sheet are approximate.

MIXING OF THE REZKLAD HP GROUT C

6 lb. 12 oz. (3.1 kg.) Unit:

Stir the contents of the resin and hardener containers prior to blending. Mix the components by hand using a clean, dry, plastic or metal container and a margin trowel. The amount of the powder may be varied within the limits stated below to adjust the mixed grout consistency. Decreasing the powder component will decrease the estimated coverage. Proportionally decrease component quantities to attain smaller batch sizes.

- Place the contents of the 1-quart can (1 lb. 8 oz. [680 g.]) of REZKLAD HP GROUT Resin in the mixing container. Scrape the sides of the resin can to remove all the resin.
- Add the contents of the 1-pint can (12 oz. [340 g.]) of REZKLAD HP GROUT Hardener. Mix the resin and hardener thoroughly for approximately two minutes.
- The amount of powder may be varied to adjust the mixed grout consistency. Add between 4 lb. 8 oz.

MIX RATIO CHART - REZKLAD HP GROUT CBatch Size: 0.27 to 0.24 ft.³ (6.8 to 5.5 ltr.)

| | Weight | | Volume | |
|--------------------------------|-----------------|-------------------------|-----------------|------------------------|
| | Parts by Weight | Weight | Parts by Volume | Volume |
| REZKLAD HP GROUT Resin | 100 | 4 lb. 12 oz. (2.2 kg.) | 100 | 62 fl. oz. (1.85 ltr.) |
| REZKLAD HP GROUT Hardener | 50 | 2 lb. 6 oz. (1.1 kg.) | 60 | 37 fl. oz. (1.10 ltr.) |
| REZKLAD HP GROUT Carbon Powder | 300 | 14 lb. 4 oz. (6.5 kg.) | 369 | 230 fl. oz. (6.8 ltr.) |
| | 270 | 12 lb. 13 oz. (5.8 kg.) | 332 | 207 fl. oz. (6.1 ltr.) |
| | 240 | 11 lb. 6 oz. (5.2 kg.) | 295 | 184 fl. oz. (5.5 ltr.) |

Proportionally increase or decrease component quantities to attain larger or smaller batch sizes.

(2.0 kg.) to 3 lb. 10 oz. (1.6 kg.) of REZKLAD HP GROUT Carbon Powder. Mix the combined components for approximately two minutes or until all the powder is thoroughly dispersed.

REZKLAD HP GROUT Carbon Powder

| Powder Ratio | Weight | Approximate Volume |
|--------------|------------------------|-------------------------|
| 300 | 4 lb. 8 oz. (2.0 kg.) | 73 fl. oz. (2.2 liters) |
| 270 | 4 lb. (1.8 kg.) | 65 fl. oz. (1.9 liters) |
| 240 | 3 lb. 10 oz. (1.6 kg.) | 58 fl. oz. (1.7 liters) |

MIXING OF THE REZKLAD HP GROUT C**21 lb. 6 oz. (9.7 kg.) Unit:**

Stir the contents of the resin and hardener containers prior to blending. Mixing of the components should be with a KOL type mixer with a 5-gallon capacity. Mixing speed should be between 60 and 75 RPM. The amount of the powder may be varied within the limits stated below to adjust the mixed grout consistency. Decreasing the powder component will decrease the estimated coverage. Refer to the Mix Ratio Chart to proportionally decrease component quantities to attain smaller batch sizes.

- Place the contents of the 1/2-gallon can (4 lb. 12 oz. [2.2 kg.]) of REZKLAD HP GROUT Resin in the 5-gallon capacity mechanical mixer. Scrape the sides of the resin can to remove all the resin.
- Add the contents of the 1/2-gallon can (2 lb. 6 oz. [1.1 kg.]) of REZKLAD HP GROUT Hardener. Mix the resin and hardener thoroughly for approximately two minutes.
- The amount of powder may be varied to adjust the mixed grout consistency. Add between 14 lb. 4 oz. (6.5 kg.) to 11 lb. 6 oz. (5.2 kg.) of REZKLAD HP GROUT Carbon Powder. Mix the combined components for approximately two minutes or until all the powder is thoroughly dispersed.

REZKLAD HP GROUT Carbon Powder

| Powder Ratio | Weight | Approximate Volume |
|--------------|-------------------------|--------------------------|
| 300 | 14 lb. 4 oz. (6.5 kg.) | 230 fl. oz. (6.8 liters) |
| 270 | 12 lb. 13 oz. (5.8 kg.) | 207 fl. oz. (6.1 liters) |
| 240 | 11 lb. 6 oz. (5.2 kg.) | 184 fl. oz. (5.5 liters) |

MIXING OF THE REZKLAD HP GROUT C**214 lb. 8 oz. (97.3 kg.) Unit:**

Stir the contents of the resin and hardener containers prior to blending. Mixing of the components should be with a KOL type mixer with a 5-gallon capacity. Mixing

speed should be between 60 and 75 RPM. The amount of the powder may be varied within the limits stated below to adjust the mixed grout consistency. Decreasing the powder component will decrease the estimated coverage. Refer to the Mix Ratio Chart to proportionally increase or decrease component quantities to attain larger or smaller batch sizes.

The following instructions are for a batch size between 21 lb. 6 oz. (9.7 kg.) to 18 lb. 8 oz. (8.49 kg.).

- Place 4 lb. 12 oz. (2.2 kg.) or 62 fluid ounces (1.85 liters) of REZKLAD HP GROUT Resin in the 5-gallon capacity mechanical mixer.
- Add 2 lb. 6 oz. (1.1 kg.) or 37 fluid ounces (1.10 liters) of REZKLAD HP GROUT Hardener. Mix the resin and hardener thoroughly for approximately two minutes.
- The amount of powder may be varied to adjust the mixed grout consistency. Add between 14 lb. 4 oz. (6.5 kg.) to 11 lb. 6 oz. (5.2 kg.) of REZKLAD HP GROUT Carbon Powder. Mix the combined components for approximately two minutes or until all the powder is thoroughly dispersed.

REZKLAD HP GROUT Carbon Powder

| Powder Ratio | Weight | Approximate Volume |
|--------------|-------------------------|--------------------------|
| 300 | 14 lb. 4 oz. (6.5 kg.) | 230 fl. oz. (6.8 liters) |
| 270 | 12 lb. 13 oz. (5.8 kg.) | 207 fl. oz. (6.1 liters) |
| 240 | 11 lb. 6 oz. (5.2 kg.) | 184 fl. oz. (5.5 liters) |

TYPICAL WORKING AND SETTING TIMES OF THE REZKLAD HP GROUT C

| Temperature | Working Time | Support Foot Traffic |
|-------------|--------------|----------------------|
| 45°F (7°C) | 65 minutes | 24 hours |
| 60°F (16°C) | 55 minutes | 9 hours |
| 75°F (24°C) | 45 minutes | 7-1/2 hours |
| 85°F (29°C) | 25 minutes | 4-1/2 hours |

APPLICATION OF THE REZKLAD HP GROUT C

- Place the freshly mixed REZKLAD HP GROUT C on the tile or pavers.
- With a rubber faced or steel trowel work the grout into the open joints.
- The rubber faced trowel or rubber squeegee is used to remove excess grout. Hold the trowel with the flat edge nearly perpendicular to the surface and pull diagonally across the grouted joints. Remove as much residue as possible from the tile surface.

RE-GROUTING ESTIMATING TABLE - REZKLAD HP GROUT C

| REZKLAD HP GROUT C - 6 lb. 12 oz. Unit Square Feet per Unit 1/4" Wide Joint x Joint Depth | | | | REZKLAD HP GROUT C - 21 lb. 6 oz. Unit Square Feet per Unit 1/4" Wide Joint x Joint Depth | | | |
|---|-----------------|-------------|------------|---|-----------------|-------------|------------|
| Joint Depth | Brick Face Size | | | Joint Depth | Brick Face Size | | |
| | 6" x 6" | 8" x 3-7/8" | 8" x 4" | | 6" x 6" | 8" x 3-7/8" | 8" x 4" |
| 3/8" | 34 sq. ft. | 30 sq. ft. | 31 sq. ft. | 3/8" | 110 sq. ft. | 97 sq. ft. | 99 sq. ft. |
| 1/2" | 26 sq. ft. | 23 sq. ft. | 23 sq. ft. | 1/2" | 82 sq. ft. | 72 sq. ft. | 74 sq. ft. |
| 5/8" | 20 sq. ft. | 18 sq. ft. | 18 sq. ft. | 5/8" | 66 sq. ft. | 58 sq. ft. | 59 sq. ft. |
| 3/4" | 17 sq. ft. | 15 sq. ft. | 15 sq. ft. | 3/4" | 55 sq. ft. | 48 sq. ft. | 49 sq. ft. |
| 1" | | 11 sq. ft. | 11 sq. ft. | 1" | | 36 sq. ft. | 37 sq. ft. |
| 1-3/16" | | 9 sq. ft. | 9 sq. ft. | 1-3/16" | | 30 sq. ft. | 31 sq. ft. |
| 1-3/8" | | 8 sq. ft. | 8 sq. ft. | 1-3/8" | | 26 sq. ft. | 27 sq. ft. |
| 1-1/2" | | | 7 sq. ft. | 1-1/2" | | | 24 sq. ft. |

A second grout pass may be required on pavers 1-3/16" thick or greater to compensate for any settling or low joints. The second pass of grout must be applied within 2 to 24 hours following the initial grout application and cleaning. Occasional voids may form by entrapped air rising to the surface. The voids should be filled upon discovery and preferably while joints are still soft.

CLEANING OF THE REZKLAD HP GROUT C

- Prepare 5-gallon pails of warm cleaning water. A small amount of liquid detergent added to warm water will aid the cleaning process.
 - Change cleaning water frequently as it becomes laden with grout residue.
 - The removal of the grout residue may begin immediately after the grout has been placed in the joint.
 - Complete the cleaning of the tile within the working time listed on the "Typical Working and Setting Times" chart.
 - Replace nylon scrub pads or cellulose sponges as they become worn or laden with excess grout residue.
 - Rubber gloves should be worn at all times.
1. Apply a small amount of warm water to the surface of the tile.
 2. Using a nylon scrub pad or cellulose sponge, loosen the grout residue from the tile with a circular motion until a white froth appears.
 3. Using a damp cellulose sponge remove the froth. Apply sufficient pressure to remove residue but not enough to pull grout from the joints.
 4. Continue the cleaning procedure frequently rinsing the cellulose sponge. Complete the cleaning with clean water until the surface is free of any haze. A damp cotton towel or wool blanket can be used by dragging it across the surface of the tile. Frequently rinse and clean the cotton towel or wool blanket. Repeat the cleaning with clean water until surface is free of any haze.

5. A cellulose sponge may be used for final touch up cleaning.

After cleaning is completed, the floor area must be kept free of liquids and contaminants until the grout can support foot traffic as listed on the "Typical Working and Setting Times" chart.

RE-GROUTING EXISTING FLOORS

REZKLAD HP GROUT C can be used to re-grout existing tile and brick floor joints and as a bond coat to set replacement or loose tile or brick.

Tile and Brick Surface Preparation: The tile or brick must be free of oils, grease, fats and other contaminants.

- a. Clean floor area with a scrub brush and a commercial grade detergent based degreasing solution. An alternate to detergent degreasers is a mixture of one pint trisodium phosphate (TSP) or sodium carbonate to two gallons of water. After scrubbing, rinse thoroughly with clean water. Repeat as necessary to remove any remaining contaminants.
- b. Remove excess and standing water by vacuuming. Follow product manufacturer's recommendations for proper use, handling and disposal of liquids.

Joint Preparation:

- a. Saw cut the joints. A 5" or 6" diameter diamond tip masonry saw blade is suggested.
Joint Width: Cut the joints the full width of the original joint to expose the side of the tile joint. Minimum joint width is 1/8" (3.2 mm.).
Joint Depth: Cut joint depth a minimum of 3/8" (9.5 mm.) deep.
- b. Remove all debris by vacuuming. Wipe tile face and tile joints with dampened sponge to remove residual dust.

Follow grouting and cleaning techniques as described in "Application of the REZKLAD HP GROUT C" and "Cleaning of the REZKLAD HP GROUT C".

CLEANING OF TOOLS AND EQUIPMENT

Steel wool, soap and warm water will remove the materials referred to in this Data Sheet from mixing tools and equipment if cleaning is done immediately after use. Solvents, such as methyl ethyl ketone, toluene or xylene, will have to be used after the material has begun to harden. Fully hardened material will have to be removed by mechanical means.

Dispose of residues and wastes in accordance with the directions in the Material Safety Data Sheets and government regulations.

STORAGE AND SHELF LIFE

Store all materials in a cool, dry environment. Keep all materials out of direct sunlight. Ideal storage temperature is 75°F (24°C). Protect from freezing. In unopened original containers, the materials referred to in this Data Sheet have a shelf life of approximately one year.

PRODUCT SPECIFICATION

The grout shall be REZKLAD HP GROUT C as manufactured by Atlas Minerals & Chemicals, Inc. The grout shall be certifiable for use in USDA inspected facilities and comply with the requirements of ASTM C658 and ANSI A118.3. The grout shall consist of an epoxy resin binder with carbon powder and be resistant to organic acids, alkalis, organic solvents and inorganic acids. During the installation, the grout shall be low odor, water cleanable and not require a wax coating for the surface of the masonry units.

PRECAUTIONS

The materials referred to in this Data Sheet are for Industrial Use Only. They contain materials that present handling and potential health hazards. Consult Material Safety Data Sheets and the container labels for complete precautionary information.

TECHNICAL SERVICES

ATLAS maintains a staff of Technical Service Representatives who are available to assist you with the use of ATLAS products. In the event of difficulties with the application of ATLAS materials, the installation should be stopped immediately and ATLAS' Technical Service Department consulted for assistance.

WARRANTY

ATLAS warrants that its products will be free from defects in workmanship and materials under normal use for a period of one (1) year from the date of shipment by ATLAS (provided the products are installed before the expiration of the shelf life). THERE ARE NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR THE PURPOSE FOR THIS PRODUCT WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ATLAS' LIABILITY FOR ALLEGED BREACH OF THIS WARRANTY SHALL BE LIMITED TO REPAIR OR REPLACEMENT OF THE DEFECTIVE PRODUCT (BUT NOT INCLUDING REMOVAL OF THE DEFECTIVE PRODUCT OR INSTALLATION OF REPLACEMENT PRODUCTS). ATLAS SHALL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES DURING THE WARRANTY PERIOD OR THEREAFTER. **ATLAS' WARRANTY IS VOIDED IF PAYMENT FOR PRODUCT IS NOT RECEIVED IN FULL.**

CHEMICAL RESISTANCE OF REZKLAD® HP GROUT C (3-37PI)

| | 80°F | 140°F |
|-------------------------------------|------|-------|
| Acetic Acid, to 10% | R | R |
| Acetic Acid, 10% to 50% | C | N |
| Acetone | C | N |
| Alum or Aluminum Sulfate | R | R |
| Ammonium Chloride, Nitrate, Sulfate | R | R |
| Ammonium Hydroxide, to 30% | R | R |
| Aniline | C | N |
| Aqua Regia | N | N |
| Barium Chloride, Sulfate | R | R |
| Beer | R | R |
| Benzene | R | R |
| Benzene Sulfonic Acid, 10% | R | R |
| Benzoic Acid | R | R |
| Black Liquor | R | R |
| Bleaching Liquor, to 2% | R | R |
| Bleaching Liquor, conc. | N | N |
| Boric Acid | R | C |
| Butter | R | R |
| Butyl Acetate | R | R |
| Butyl Alcohol | R | R |
| Butyric Acid | C | N |
| Calcium Chloride, Nitrate, Sulfate | R | R |
| Calcium Hydroxide | R | R |
| Calcium Hypochlorite | R | C |
| Casein | R | R |
| Chlorine, Dry | C | - |
| Chlorine, Wet | C | - |
| Chlorine Water | R | - |
| Chloroacetic Acid, to 10% | C | C |
| Chloroform | R | - |
| Chromic Acid, to 30% | R | C |
| Citric Acid, to 10% | R | R |
| Copper Chloride, Nitrate, Sulfate | R | R |
| Ecolab "Lift II" | R | R |
| Ecolab "XY12" | R | R |
| Ecolab "HC-10" | R | R |
| Ecolab "Ster-bac" | R | R |
| Ecolab "P3Oxonia" | R | R |
| Ecolab "Enforce" | R | R |
| Ether | R | - |
| Ethyl Acetate | C | - |
| Ethyl Alcohol | R | C |
| Ethylene Dichloride | C | - |
| Ethylene Glycol | R | R |
| Fatty Acids | C | C |
| Ferric Chloride, Nitrate, Sulfate | R | R |
| Fluosiilic Acid, 30% | R | R |

| | 80°F | 140°F |
|--------------------------------------|------|-------|
| Formaldehyde, to 37% | R | R |
| Formic Acid, 10% | R | C |
| Grape Juice | R | R |
| Hydrobromic Acid, to 20% | R | R |
| Hydrochloric Acid, to 37% | R | R |
| Hydrofluoric Acid, to 20% | R | C |
| Hydrogen Peroxide | R | - |
| Hypochlorous Acid, to 5% | R | C |
| Jet Fuel | R | - |
| Kerosene | R | - |
| Lactic Acid, to 10% | R | C |
| Lactic Acid, above 10% | N | N |
| Lard | R | R |
| Lux Liquid | R | R |
| Magnesium Chloride, Nitrate, Sulfate | R | R |
| Maleic Acid | C | C |
| Methyl Alcohol | C | C |
| Methylene Chloride | N | - |
| Methyl Ethyl Ketone | N | - |
| Milk | R | R |
| Mineral Oil | R | R |
| Nickel Chloride, Nitrate, Sulfate | R | R |
| Nitric Acid, to 30% | R | R |
| Oleic Acid | C | C |
| Oxalic Acid | R | C |
| Peracetic Acid, 1% | R | R |
| Perchloroethylene | C | C |
| Petroleum | R | R |
| Phenol, to 5% | C | - |
| Phosphoric Acid | R | R |
| Picric Acid, to 5% | R | N |
| Potassium Chloride, Nitrate, Sulfate | R | R |
| Potassium Hydroxide, to 25% | R | R |
| Potassium Hydroxide, 25% to 50% | R | R |
| Salt, Saturated Solution | R | R |
| Sodium Bicarbonate, Carbonate | R | R |
| Sodium Chloride, Nitrate, Phosphate | R | R |
| Sodium Sulfate, Sulfide | R | R |
| Sodium Hydroxide, to 25% | R | R |
| Sodium Hydroxide, 25% to 50% | R | R |
| Sodium Hypochlorite, to 6% | R | R |
| Sodium Hypochlorite, 6% to 12% | R | - |
| Stannic Chloride | R | N |
| Stearic Acid | C | C |
| Sugar, Saturated Solution | R | R |
| Sulfuric Acid, to 93% | R | C |
| Sulfurous Acid, to 10% | R | R |

| | 80°F | 140°F |
|---|------|-------|
| Toluene | R | R |
| Toluene Sulfonic Acid | R | C |
| Tomato Juice | R | R |
| 1,1,1-Trichloroethane | R | R |
| Trisodium Phosphate | R | R |
| Turpentine | R | - |
| Urea, to 20% | R | R |
| Urine | R | C |
| Vegetable Oil | R | R |
| Vinegar | R | R |
| Water, Fresh | R | R |
| Water, Distilled | R | R |
| Water and Sewage | R | R |
| Xylene | R | R |
| Zinc Chloride, Nitrate, Sulfate (6-03 ²) | R | R |

KEY

- R - Recommended
- N - Not Recommended
- C - Conditional; May be serviceable if the contaminant is immediately removed or washed off the surface.

Note - The information presented in the chemical resistance tables is based on judgments derived from laboratory testing and field service performance. The tables have been prepared as a guide to performance. No guarantee of results is made or implied and no liability in connection with this information is assumed. In actual service, floors and walls protected with REZKLAD HP GROUT C are subjected to splash and spillage, as well as dilution effects of wash water, mixing with other solutions, wetting and drying cycles, temperature cycling and cleaning procedures.

For immersion service, contact ATLAS for recommendation. The information presented herein should be supplemented by in-service testing. The data furnished in the tables may be revised on the basis of further testing.