



Atlas Minerals & Chemicals, Inc.



DATA SHEET

7-601PI (6-03²)
Supersedes 7-601PI (3-02)

REZKLAD® E-HI BUILD 90 / REZKLAD® E-HI BUILD 90 LT

DESCRIPTION

REZKLAD E-HI BUILD 90 is a corrosion resistant high solids epoxy coating for floors and walls. The durable coating is designed for application to concrete and carbon steel substrates. REZKLAD E-HI BUILD 90 is roller, squeegee or brush applied at thicknesses of 5 mils (0.13 mm.) to 15 mils (0.38 mm.) per coat.

TYPICAL USES

REZKLAD E-HI BUILD 90 is an excellent flooring system. It's also excellent as a wall coating or coating for steel structures and as a sealer coat over monolithic floor toppings. REZKLAD E-HI BUILD 90 is designed for chemical, splash and spill environments providing a durable, economical coating system. The versatile easy-to-apply coating is excellent for foot or light forklift traffic areas and as a topcoat over monolithic floor toppings. The system can be furnished with a variety of easy-to-clean finishes. REZKLAD E-HI BUILD 90 can be applied to vertical concrete or steel substrates, such as walls and structural steel columns subjected to chemical splashing and fumes. REZKLAD E-HI BUILD 90 is excellent for food process, deli / bakery, assembly, light manufacturing and warehouse areas, laboratories, mechanical equipment rooms and clean rooms. REZKLAD E-HI BUILD 90 is certifiable for use in USDA inspected facilities.

CHEMICAL RESISTANCE

REZKLAD E-HI BUILD 90 is resistant to splash and spills of many acids, alkalies, salts, oils, greases and food chemicals. Refer to the chemical resistance chart for specific information.

Note: ATLAS chemical resistance data is derived from testing in total immersion service.

METHOD OF INSTALLATION

REZKLAD E-HI BUILD 90 is designed to be applied with a roller, squeegee or brush over concrete or carbon steel substrates. REZKLAD E-HI BUILD 90 is typically applied from 10 mils (0.25 mm.) to 15 mils (0.38 mm.) per coat on horizontal surfaces and 5 mils (0.13 mm.) to 10 mils (0.25 mm.) on vertical surfaces. Slip resistant floor finishes are achieved by broadcasting ATLAS® AGGREGATE into the wet basecoat and sealed with a second coat of REZKLAD E-HI BUILD 90.

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUE
% Solids	ATM No. 14	91-93
Temperature Resistance, as a Coating over Concrete* Continual Intermittent		140°F (60°C) 200°F (93°C)
Abrasion Resistance, Taber CS-17 wh., 1 kg., 1,000 cyc. Smooth Finish Broadcast to Excess	ASTM C501	97 85
Hardness, Shore D-2	ASTM D2240	70-75

*When applied over an epoxy monolithic floor topping, temperature resistance may vary.

AVAILABLE COLORS

Standard colors of REZKLAD E-HI BUILD 90 are gray, red and tan. Custom colors are available upon request.

PACKAGING AND COVERAGE

REZKLAD E-CONCRETE PRIMER

1/2-Gallon Unit (3 lb. 7 oz. [1.6 kg.]) Consisting of:

One - 1/2-gal. can of Resin (2 lb. 8 oz. [1.1 kg.])

One - 1-pt. can of Hardener (15 oz. [425 g.])

Coverage: Approx. 100 sq. ft. (9.3 m²) per unit

1-1/2 Gal. Unit (12 lb. 2 oz. [5.5 kg.]) Consisting of:

One - 1-gal. can of Resin (9 lb. [4.1 kg.])

One - 1/2-gal. can of Hardener (3 lb. 2 oz. [1.4 kg.])

Coverage: Approx. 350 sq. ft. (32.5 m²) per unit

REZKLAD E-CONCRETE PRIMER LT

1/2-Gallon Unit (3 lb. 12 oz. [1.7 kg.]) Consisting of:

One - 1/2-gal. can of Resin (2 lb. 8 oz. [1.1 kg.])

One - 1-qt. can of LT Hardener (1 lb. 4 oz. [567 g.])

Coverage: Approx. 110 sq. ft. (10.2 m²) per unit

Coverage as Conductive Primer: Approx. 65 sq. ft. (6.0 m²) per unit

1-1/2-Gallon Unit (13 lb. 8 oz. [6.1 kg.]) Consisting of:

One - 1-gal. can of Resin (9 lb. [4.1 kg.])

One - 1-gal. can of LT Hardener (4 lb. 8 oz. [2.0 kg.])

Coverage: Approx. 400 sq. ft. (37.2 m²) per unit

Coverage as Conductive Primer: Approx. 240 sq. ft. (22.3 m²) per unit

REZKLAD E-HI BUILD 90

1-1/2-Gal. Unit (15 lb. 8 oz. [7.0 kg.]) Consisting of:

One - 1-gal. can of Resin (12 lb. [5.4 kg.])

One - 1/2-gal. can of Hardener (3 lb. 8 oz. [1.6 kg.])

7-Gallon Unit (77 lb. 8 oz. [35.2 kg.]) Consisting of:

One - 5-gal. pail of Resin (60 lb. [27.2 kg.])
 Five - 1/2-gal. cans of Hardener (3 lb. 8 oz. [1.6 kg.]) ea.

COVERAGE OF THE REZKLAD E-HI BUILD 90

Unit Size	5 mils	10 mils	Over Aggregate
1-1/2 Gallon	450 sq. ft.	225 sq. ft.	170 sq. ft.
7-Gallon	2,250 sq. ft.	1,125 sq. ft.	865 sq. ft.

REZKLAD E-HI BUILD 90 LT**1-1/2-Gal. Unit (14 lb. 12 oz. [6.7 kg.]) Consisting of:**

One - 1-gal. can of Resin (12 lb. [5.4 kg.])
 One - 1/2-gal. can of LT Hardener (2 lb. 12 oz. [1.2 kg.])

7-Gallon Unit (73 lb. 12 oz. [33.5 kg.]) Consisting of:

One - 5-gal. pail of Resin (60 lb. [27.2 kg.])
 Five - 1/2-gal. cans of LT Hardener (2 lb. 12 oz. [1.2 kg.]) ea.

COVERAGE OF THE REZKLAD E-HI BUILD 90 LT

Unit Size	5 mils	10 mils	Over Aggregate
1-1/2 Gallon	450 sq. ft.	225 sq. ft.	170 sq. ft.
7-Gallon	2,250 sq. ft.	1,125 sq. ft.	865 sq. ft.

ATLAS AGGREGATE No. 8 (Fine Finish)

One - bag (100 lb. [45.4 kg.])
 Coverage broadcast to excess: Approx. 500 sq. ft. (46.5 m²) per bag
 Coverage light broadcast: Approx. 2,000 sq. ft. (186 m²) per bag

ATLAS AGGREGATE No. 2 (Coarse Finish)

One - bag (100 lb. [45.4 kg.])
 Coverage broadcast to excess: Approx. 500 sq. ft. (46.5 m²) per bag
 Coverage light broadcast: Approx. 2,000 sq. ft. (186 m²) per bag

UREKLAD® 210

1-gal. can (7 lb. 14 oz. [3.6 kg.])
 Coverage over smooth surface: Approx. 300 sq. ft. (27.9 m²) per unit @ 2 mils (0.05 mm.)

5-gal. pail (39 lb. 6 oz. [17.9 kg.])

Coverage over smooth surface: Approx. 1,500 sq. ft. (139 m²) per unit @ 2 mils (0.05 mm.)

SURFACE PREPARATION

REZKLAD E-HI BUILD 90 can be applied to concrete and metal surfaces. The substrate must be structurally sound, clean, dry and free of all contaminants, such as sealers, curing compounds, coatings, oil, dirt, dust and water. Previously applied coatings or paint must be removed.

Concrete: Finished concrete must be free of ridges, protrusions, fins, mortar splatter and have a tight laitance-

free steel trowel finish. Abrasive grit blasting is recommended. Where impractical, chemical preparation by acid washing is acceptable. A finish similar to the profile of 100 to 120 grit sandpaper is suggested.

Metals: Metal surfaces should be grit blasted to a NACE #1 white metal blast cleaned surface finish. When grit blasting is not practical, clean by wire brushing or with abrasive paper and wash with degreasing solvent such as xylene. For additional information, refer to Surface Preparation, Data Sheet PS-30.

TEMPERATURE DURING APPLICATION

Store REZKLAD E-HI BUILD 90 and REZKLAD E-CONCRETE PRIMER at 70°F (21°C) to 80°F (27°C) for 24 hours prior to use. The best working characteristics of the materials will be attained when the temperature of the substrate, air, REZKLAD E-HI BUILD 90 and REZKLAD E-CONCRETE PRIMER are between 65°F (18°C) and 85°F (29°C).

Minimum temperature for installation is 65°F (18°C). At temperatures below 65°F (18°C), use REZKLAD E-CONCRETE PRIMER LT AND REZKLAD E-HI BUILD 90 LT.

Do not apply when relative humidity is greater than 75% or on substrates that can flex.

REZKLAD E-CONCRETE PRIMER

REZKLAD E-CONCRETE PRIMER is not required if the REZKLAD E-HI BUILD 90 is to be applied to properly prepared new and cured concrete substrates or grit blasted carbon steel substrates as described in Surface Preparation, Data Sheet PS-30. REZKLAD E-CONCRETE PRIMER must be applied to all other conditions of concrete substrates after proper surface preparation.

TYPICAL WORKING & DRYING TIMES OF THE REZKLAD E-CONCRETE PRIMER

Temperature	Working Time	Minimum Drying Time	Maximum Drying Time
65°F (18°C)	35 min.	12 hours	48 hours
75°F (24°C)	25 min.	8 hours	48 hours
85°F (29°C)	15 min.	6 hours	24 hours

MIXING AND APPLICATION OF THE REZKLAD E-CONCRETE PRIMER

Stir the contents of the individual resin and hardener containers prior to blending. Mixing of the components should be done with a hand drill equipped with a "Jiffy" type mixer at a mixing speed between 300 and 500 RPM. During mixing, move the mixing blade in circular and up and down motions scraping all sides and the bottom of the mixing container.

- Combine the contents of the cans of REZKLAD E-CONCRETE PRIMER Resin and Hardener in a suitable mixing container. Mix thoroughly for one minute.
- Apply REZKLAD E-CONCRETE PRIMER with a brush or short nap roller making sure to work it into the pores of the concrete. Do not allow puddling.

MIX RATIO CHART - REZKLAD E-CONCRETE PRIMER

REZKLAD E-CONCRETE PRIMER	Weight	Volume
REZKLAD E-CONCRETE PRIMER Resin	2 lb. 8 oz. (1.1 kg.)	34.6 fl. oz. (1.0 liters)
REZKLAD E-CONCRETE PRIMER Hardener	15 oz. (425 g.)	13.7 fl. oz. (0.41 liters)
Batch Size	3 lb. 7 oz. (1.6 kg.)	48.3 fl. oz. (1.4 liters)

MIX RATIO CHART - REZKLAD E-CONCRETE PRIMER LT

REZKLAD E-CONCRETE PRIMER LT	Weight	Volume
REZKLAD E-CONCRETE PRIMER Resin	9 lb. (4.1 kg.)	125 fl. oz. (3.7 liters)
REZKLAD E-CONCRETE PRIMER LT Hardener	4 lb. 8 oz. (2.0 kg.)	70 fl. oz. (2.07 liters)
Batch Size	13 lb. 8 oz. (6.1 kg.)	195 fl. oz. (5.8 liters)

MIX RATIO CHART - REZKLAD E-HI BUILD 90

REZKLAD E-HI BUILD 90	Weight	Volume
REZKLAD E-HI BUILD 90 Resin	12 lb. (5.4 kg.)	124 fl. oz. (3.7 liters)
REZKLAD E-HI BUILD 90 Hardener	3 lb. 8 oz. (1.6 kg.)	56 fl. oz. (1.7 liters)
Batch Size	15 lb. 8 oz. (7.0 kg.)	180 fl. oz. (5.3 liters)

MIX RATIO CHART - REZKLAD E-HI BUILD 90 LT

REZKLAD E-HI BUILD 90 LT	Weight	Volume
REZKLAD E-HI BUILD 90 Resin	12 lb. (5.4 kg.)	124 fl. oz. (3.7 liters)
REZKLAD E-HI BUILD 90 LT Hardener	2 lb. 12 oz. (1.2 kg.)	40 fl. oz. (1.2 liters)
Batch Size	14 lb. 12 oz. (6.7 kg.)	164 fl. oz. (4.9 liters)

- c. The primed surface should be tacky or dry before applying REZKLAD E-HI BUILD 90. If the primer is allowed to dry for longer than the maximum drying time, the surface must be sanded and the area reprimed before proceeding.

TYPICAL WORKING AND DRYING TIMES OF THE REZKLAD E-CONCRETE PRIMER LT

Temperature	Working Time	Tack Free	Maximum Drying Time
34°F (1°C)	35 min.	24 hrs.	48 hrs.
40°F (4°C)	25 min.	16 hrs.	48 hrs.
50°F (10°C)	20 min.	12 hrs.	24 hrs.
60°F (16°C)	15 min.	10 hrs.	24 hrs.
70°F (21°C)	10 min.	6 hrs.	24 hrs.

MIXING OF THE REZKLAD E-CONCRETE PRIMER LT

Stir the contents of the individual resin and hardener containers prior to blending. Mixing of the components should be done with a hand drill equipped with a "Jiffy" type mixer at a mixing speed between 300 and 500 RPM. During mixing, move the mixing blade in circular and up and down motions scraping all sides and the bottom of the mixing container.

1/2-Gallon Unit of Rezklad E-Concrete Primer LT:

- a. Place the contents of the 1/2-gallon can (2 lb. 8 oz. [1.1 kg.]) of REZKLAD E-CONCRETE

PRIMER Resin in a clean, dry plastic or metal mixing container. Scrape the sides of the resin can to remove all the resin.

- b. Add the contents of the 1-quart can (1 lb. 4 oz. [567 g.]) of REZKLAD E-CONCRETE PRIMER LT Hardener. Scrape the sides of the hardener can to remove all the hardener.
- c. Mix the resin and hardener thoroughly for approximately two minutes.

1-1/2-Gallon of Rezklad E-Concrete Primer LT:

- a. Place the contents of the 1-gallon can (9 lb. [4.1 kg.]) of REZKLAD E-CONCRETE PRIMER Resin in a clean, dry plastic or metal mixing container. Scrape the sides of the resin can to remove all the resin.
- b. Add the contents of the 1-gallon can (4 lb. 8 oz. [2.0 kg.]) of REZKLAD E-CONCRETE PRIMER LT Hardener. Scrape the sides of the hardener can to remove all the hardener.
- c. Mix the resin and hardener thoroughly for approximately two minutes.

MIXING OF THE REZKLAD E-HI BUILD 90

Stir the contents of the individual resin and hardener containers prior to blending. Mixing of the components should be done by hand with a paint stirrer or with a hand drill equipped with a "Jiffy" type mixer at a mixing speed between 300 and 500 RPM. During mixing, move the mixing blade in circular and

TYPICAL WORKING & DRYING TIMES OF THE REZKLAD E-HI BUILD 90

Temperature	Working Time	Support Foot Traffic	Maximum Drying Time*
65°F (18°C)	35 min.	16 hours	48 hours
75°F (24°C)	25 min.	8 hours	36 hours
85°F (29°C)	15 min.	6 hours	24 hours

*Maximum Drying Time listed is for drying time between recoats

up and down motions scraping all sides and the bottom of the mixing container.

1-1/2-Gallon Unit (15 lb. 8 oz. [7.0 kg.]):

- Combine the contents of the 1-gallon can (12 lb. [5.4 kg.]) of REZKLAD E-HI BUILD 90 Resin with the 1/2-gallon can (3 lb. 8 oz. [1.6 kg.]) of REZKLAD E-HI BUILD 90 Hardener in a clean, dry plastic or metal container.
- Mix thoroughly for approximately two minutes.

7-Gallon Unit (77 lb. 8 oz. [35.2 kg.]):

The following mixing instructions are for a batch size of 1.4 gallons (5.3 liters) or 15 lb. 8 oz. (7.0 kg.). Proportionally increase or decrease component quantities to attain larger or smaller batch sizes.

- Combine 124 fluid ounces (3.7 liters) of REZKLAD E-HI BUILD 90 Resin with 56 fluid ounces (1.7 liters) REZKLAD E-HI BUILD 90 Hardener in a suitable mixing container.
- Mix thoroughly for two minutes as described above.

MIX RATIO OF THE REZKLAD E-HI BUILD 90

	by Weight	by Volume
Rezklad E-Hi Build 90 Resin	100	100
Rezklad E-Hi Build 90 Hardener	29	46

MIXING OF THE REZKLAD E-HI BUILD 90 LT

Stir the contents of the individual resin and hardener containers prior to blending. Mixing of the components should be done by hand with a paint stirrer or with a hand drill equipped with a "Jiffy" type mixer at a mixing speed between 300 and 500 RPM. During mixing, move the mixing blade in circular and up and down motions scraping all sides and the bottom of the mixing container.

1-1/2-Gallon Unit (14 lb. 12 oz. [6.7 kg.]):

- Combine the contents of the 1-gallon can (12 lb. [5.4 kg.]) of REZKLAD E-HI BUILD 90 Resin with the 1/2-gallon can (2 lb. 12 oz. [1.2 kg.]) of REZKLAD E-HI BUILD 90 LT Hardener in a clean, dry plastic or metal container.
- Mix thoroughly for approximately two minutes.

7-Gallon Unit (73 lb. 12 oz. [33.5 kg.]):

The following mixing instructions are for a batch size of 1.3 gallons (4.9 liters) or 14 lb. 12 oz. (6.7 kg.). Proportionally increase or decrease component quantities to attain larger or smaller batch sizes.

- Combine 124 fluid ounces (3.7 liters) of REZKLAD E-HI BUILD 90 Resin with 40 fluid ounces (1.2 liters) of REZKLAD E-HI BUILD 90 LT Hardener in a suitable mixing container.
- Mix thoroughly for two minutes as described above.

MIX RATIO OF THE REZKLAD E-HI BUILD 90 LT

	by Weight	by Volume
Rezklad E-Hi Build 90 Resin	100	100
Rezklad E-Hi Build 90 LT Hardener	22.5	32.5

TYPICAL WORKING & DRYING TIMES OF THE REZKLAD E-HI BUILD 90 LT

Temperature	Working Time	Support Foot Traffic	Maximum Drying Time*
34°F (1°C)	35 min.	24 hours	48 hours
40°F (4°C)	30 min.	18 hours	48 hours
50°F (10°C)	25 min.	12 hours	24 hours
60°F (16°C)	20 min.	10 hours	24 hours
70°F (21°C)	15 min.	8 hours	24 hours

*Maximum Drying Time listed is for drying time between recoats

APPLICATION OF THE REZKLAD E-HI BUILD 90

REZKLAD E-CONCRETE PRIMER is not required if the REZKLAD E-HI BUILD 90 is to be applied to properly prepared new and cured concrete substrates or grit blasted carbon steel substrates as described in Surface Preparation, Data Sheet PS-30. REZKLAD E-CONCRETE PRIMER must be applied to all other conditions of concrete substrates after proper surface preparation.

Apply a topcoat or slip resistant surface of REZKLAD E-HI BUILD 90 within 48 hours of the application of the epoxy monolithic floor topping. If REZKLAD E-HI BUILD 90 is to be applied over the epoxy monolithic floor topping that has been installed for more than 48 hours, the topping surface must first be sanded, cleaned and primed with REZKLAD E-CONCRETE PRIMER. Apply the primer as described in "Mixing and Application of the REZKLAD E-CONCRETE PRIMER".

Topcoat over an Epoxy Monolithic Floor Topping*:

- Apply a 5 mil (13 mm.) coat of REZKLAD E-HI BUILD 90. Spread with a flat rubber squeegee or the edge of a steel trowel.
- Immediately back roll with a short nap roller.
- Fill any pinholes or other defects with a second application of REZKLAD E-HI BUILD 90.

Slip Resistant Surface over an Epoxy Monolithic Floor Topping*:

- Apply a 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a medium nap roller.
- Within 10 minutes, broadcast ATLAS AGGREGATE into the wet REZKLAD E-HI BUILD 90. The aggregate can be broadcast in a range from light to excess. The amount of

aggregate and size of aggregate will determine the finished texture.

- c. After the REZKLAD E-HI BUILD 90 can support foot traffic, vacuum or sweep to remove any unbonded aggregate.
- d. Apply a second 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a flat rubber squeegee or short nap roller.

Smooth Coating (no aggregate) over Concrete or Steel*:

- a. Determine substrate conditions. If recommended, apply REZKLAD E-CONCRETE PRIMER with a short nap roller as described in "Mixing and Application of the REZKLAD E-CONCRETE PRIMER".
- b. Apply a 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a medium nap roller.
- c. After REZKLAD E-HI BUILD 90 can support foot traffic, apply a second 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a flat rubber squeegee or short nap roller.

Slip Resistant Coating over Concrete or Steel*:

- a. Determine substrate conditions. If recommended, apply REZKLAD E-CONCRETE PRIMER with a short nap roller as described in "Mixing and Application of the REZKLAD E-CONCRETE PRIMER".
- b. Apply a 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a medium nap roller.
- c. Within 10 minutes, broadcast ATLAS AGGREGATE into the wet REZKLAD E-HI BUILD 90. The aggregate can be broadcast in a range from light to excess. The amount of aggregate and size of aggregate will determine the finished texture.
- d. After the REZKLAD E-HI BUILD 90 can support foot traffic, vacuum or sweep to remove any unbonded aggregate.
- e. Apply a second 10 mil (0.25 mm.) to 15 mil (0.38 mm.) coat of REZKLAD E-HI BUILD 90 with a flat rubber squeegee or short nap roller.

***Note:** If the REZKLAD E-CONCRETE PRIMER or REZKLAD E-HI BUILD 90 are allowed to dry for longer than the maximum drying time, the surface must be sanded and cleaned before proceeding to the next step.

OPTIONAL SURFACE FINISHES

SMOOTH: If a smoother, less textured surface is required, apply additional coats of REZKLAD E-HI BUILD 90 with a short nap roller until desired finish is attained.

SCRATCH-RESISTANT: An optional coat of UREKLAD 210 can be applied for added scratch resistance. Apply the one component UREKLAD 210 with a short nap roller. UREKLAD 210 will support foot traffic in approximately 5 hours at 75°F (24°C).

CLEANING OF TOOLS AND EQUIPMENT

Steel wool, soap and warm water will remove the materials referred to in this Data Sheet from mixing tools and equipment if cleaning is done immediately after use. Solvents, such as methyl ethyl ketone, toluene or xylene, will have to be used after the material has begun to harden. Fully hardened material will have to be removed by mechanical means.

Dispose of residues and wastes in accordance with the directions in the Material Safety Data Sheets and government regulations.

STORAGE AND SHELF LIFE

Store all materials in a cool, dry environment. Keep all materials out of direct sunlight. Ideal storage temperature is 75°F (24°C). Protect from freezing. In unopened original containers, the materials referred to in this Data Sheet have a shelf life of approximately one year.

PRODUCT SPECIFICATION

The system shall be REZKLAD E-HI BUILD 90 or REZKLAD E-HI BUILD 90 LT as manufactured by Atlas Minerals & Chemicals, Inc.

PRECAUTIONS

The materials referred to in this Data Sheet are for Industrial Use Only. They contain materials that present handling and potential health hazards. Consult Material Safety Data Sheets and the container labels for complete precautionary information.

TECHNICAL SERVICES

ATLAS maintains a staff of Technical Service Representatives who are available to assist you with the use of ATLAS products. In the event of difficulties with the application of ATLAS materials, the installation should be stopped immediately and ATLAS' Technical Service Department consulted for assistance.

WARRANTY

ATLAS warrants that its products will be free from defects in workmanship and materials under normal use for a period of one (1) year from the date of shipment by ATLAS (provided the products are installed before the expiration of the shelf life). THERE ARE NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR THE PURPOSE FOR THIS PRODUCT WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ATLAS' LIABILITY FOR ALLEGED BREACH OF THIS WARRANTY SHALL BE LIMITED TO REPAIR OR REPLACEMENT OF THE DEFECTIVE PRODUCT (BUT NOT INCLUDING REMOVAL OF THE DEFECTIVE PRODUCT OR INSTALLATION OF REPLACEMENT PRODUCTS). ATLAS SHALL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES DURING THE WARRANTY PERIOD OR THEREAFTER. **ATLAS' WARRANTY IS VOIDED IF PAYMENT FOR PRODUCT IS NOT RECEIVED IN FULL.**

CHEMICAL RESISTANCE OF REZKLAD® E-HI BUILD 90 / REZKLAD® E-HI BUILD 90 LT (7-601PI)

Acetic Acid, to 5%	E	Fatty Acids	C	Nitric Acid, 5% to 10%	C	Trichloroethylene	C
Acetic Acid, to 10%	F	Ferric Chloride, Nitrate, Sulfate	E	Oleic Acid	C	Trisodium Phosphate	E
Acetic Acid, 10% to 50%	C	Fluosiilic Acid	C	Olive Oil	C	Tung Oil	F
Acetone	C	Formaldehyde	E	Oxalic Acid	G	Turpentine	G
Alum or Aluminum Sulfate	E	Formic Acid, 10%	F	Pectin	E	Urea	E
Ammonium Chloride, Nitrate, Sulfate	E	Fruit Extracts	F	Perchloroethylene	C	Urine	G
Ammonium Hydroxide, to 10%	E	Fruit Juices	F	Petroleum	E	Vegetable Oil	C
Ammonium Hydroxide, 10% to 30%	G	Gasoline	E	Phenol, to 5%	C	Vinegar	E
Aniline	N	Glucose	F	Phosphoric Acid, to 25%	E	Water, Distilled	E
Animal Oils	C	Glycerine	G	Phosphoric Acid, 25% to 50%	G	Water, Fresh	E
Bakery Products	G	Grape Juice	F	Phosphoric Acid, above 50%	C	Water and Sewage	G
Barium Chloride, Sulfate	E	Horse Radish	E	Pickles	E	Wine	G
Beer	E	Hydrobromic Acid, to 20%	G	Picric Acid, to 5%	E	Xylene	F
Benzene	C	Hydrochloric Acid, to 20%	E	Potassium Bicarbonate, Carbonate	E	Yeast	E
Benzene Sulfonic Acid, 10%	E	Hydrochloric Acid, 20% to 37%	G	Potassium Chloride, Nitrate, Sulfate	E	Zinc Chloride, Nitrate, Sulfate	E
Benzoic Acid	E	Hydrofluoric Acid, to 20%	C	Potassium Hydroxide, to 25%	E	(6-03 ²)	
Black Liquor	E	Hydrofluoric Acid, 20% to 70%	N	Potassium Hydroxide, 25% to 50%	F		
Boric Acid	E	Hydrofluosilicic Acid	C	Salad Oils	C		
Bromine Water	C	Hydrogen Peroxide	G	Salicylic Acid	G		
Butter	C	Hypocholeous Acid, to 5%	F	Shortening	C		
Butyl Acetate	C	Ice Cream	E	Silver Nitrate	G		
Butyl Alcohol	C	Jams & Jellies	F	Skydrol	G		
Butyric Acid	C	Jet Fuel	E	Smokehouse Residues	F		
Calcium Chloride, Nitrate, Sulfate	E	Kerosene	E	Sodium Bicarbonate, Carbonate	E		
Calcium Hydroxide	E	Ketchup	G	Sodium Bisulfate, Sulfate	E		
Calcium Hypochlorite	F	Lactic Acid, to 5%	G	Sodium Chloride, Nitrate, Phosphate	E		
Carbonated Water	E	Lactic Acid, 5% to 10%	F	Sodium Hydroxide, to 25%	E		
Casein	G	Lactic Acid, above 10%	C	Sodium Hydroxide, 25% to 50%	F		
Cheese, all	G	Lard	C	Sodium Hypochlorite	F		
Chlorine, Dry or Wet	F	Linseed Oil	F	Sodium Sulfide, Sulfite	G		
Chlorine Water	E	Lux Liquid	E	Sodium Thiosulfate	E		
Chloroacetic Acid, to 10%	C	Magnesium Chloride, Nitrate, Sulfate	E	Soft Drink Concentrates	C		
Chloroform	N	Magnesium Hydroxide	E	Soft Drinks	G		
Chromic Acid, to 5%	F	Maleic Acid, 25%	C	Soups	E		
Chromic Acid, 5% to 10%	C	Malt	G	Soya Oil	C		
Cider	F	Malt Liquors	G	Stearic Acid	E		
Citric Acid, to 10%	G	Margarine	C	Sugar, Saturated Solution	F		
Citrus Fruits	G	Methyl Alcohol	E	Sulfuric Acid, to 20%	E		
Coffee	E	Methyl Ethyl Ketone	N	Sulfuric Acid, 20% to 50%	G		
Copper Chloride, Nitrate, Sulfate	E	Methylene Chloride	N	Sulfuric Acid, above 50%	C		
Corn Oil	G	Milk	E	Sulfurous Acid	E		
Corn Syrup	G	Mineral Oil	E	Syrup	C		
Egg Yolk	E	Mineral Spirits	E	Tannic Acid	G		
Ethyl Acetate	C	Molasses	F	Tartaric Acid	G		
Ethyl Alcohol	E	Muriatic Acid	G	Tea	E		
Ethyl Ether	F	Mustard	G	Toluene	F		
Ethylene Dichloride	N	Nickel Chloride, Nitrate, Sulfate	E	Toluene Sulfonic Acid	F		
Ethylene Glycol	G	Nitric Acid, to 5%	F	Tomato Juice	G		

KEY

- E - Excellent
- G - Good
- F - Fair
- N - Not Recommended
- C - Conditional; May be serviceable if the contaminant is immediately removed or washed off the surface.

Note - The information presented in the chemical resistance tables is based on judgments derived from laboratory testing in total immersion service.

The tables have been prepared as a guide to performance. No guarantee of results is made or implied and no liability in connection with this information is assumed. In actual service, floors and walls protected with REZKLAD E-HI BUILD 90 are subjected to splash and spillage, as well as dilution effects of wash water, mixing with other solutions, wetting and drying cycles, temperature cycling and cleaning procedures. For immersion service, contact ATLAS for recommendation. The information presented herein should be supplemented by in-service testing. The data furnished in the tables may be revised on the basis of further testing.