

# **DATA SHEET**

AM-211 / AM-210 (4-00<sup>2</sup>) Supersedes AM-211 / AM-210 (10-99)



## WATERPROOFING ASPHALT WA-1 (AM-211) AND WM-1 (AM-210)

#### **DESCRIPTION**

WATERPROOFING ASPHALT WA-1 and WM-1 are hot applied, waterproofing, one component products that meet the specifications of the Pennsylvania Department of Transportation (PENNDOT).

The asphalt cement shall not be heated in excess of 400°F (204°C) and shall be agitated while heating to prevent localized overheating.

CUTBACK ASPHALT PRIMER WP-1 is a one-component primer that also meets the specifications of the PENNDOT.

The specifications for these products are:

| Test Method           | WA-1            | WM-1             | Test                     | WP-1              |
|-----------------------|-----------------|------------------|--------------------------|-------------------|
| Flash Point           | 350°F minimum   | 400°F minimum    | Water                    | 0% maximum        |
| Softening Point       | 115°F to 145°F  | 145°F to 171°F   | Furol Visc @ 25°C        | 25 to 150 seconds |
| Penetration @ 39°F    | _               | 12 dmm. minimum  | Solubility in TCE        | 99% minimum       |
| Penetration @ 77°F    | 50 to 100 dmm.  | 25 to 50 dmm.    | Distillation (% by vol.) |                   |
| Penetration @ 115°F   | _               | 115 dmm. maximum | 0 - 225°C (437°F)        | 35% minimum       |
| Ductility @ 60°F      | 50 cm. minimum  | _                | 0 - 360°C (680°F)        | 65% maximum       |
| Ductility @ 77°F      | _               | 15 cm. minimum   | 77 Pen on Residue        |                   |
| Water Content         | None            | None             | After Distillation       | 20 to 50 dmm.     |
| Solubility in TCE     | 99% minimum     | 99% minimum      |                          |                   |
| Loss on Heating*      | 2% maximum      | 1% maximum       |                          |                   |
| Retained Penetration* | 60% of original | 60% of original  |                          |                   |

<sup>\*50-</sup>gram sample heated for five (5) hours at 325°F

### **PACKAGING**

55-gallon Metal Drum

Fibre Carton Approx. 100 lb. (45.4 kg.)

Approx. 100 lb. (45.4 kg.)
Approx. 420 lb. (190.5 kg.)
Approx. 420 lb. (190.5 kg.)

WM-1

WP-1 (5-gal. pail) – 35 lb. (15.9 kg.) WP-1 (55-gal. drum) – 350 lb. (158.6 kg.)

#### WARRANTY

ATLAS warrants that its products will be free from defects in workmanship and materials under normal use for a period of one (1) year from the date of shipment by ATLAS (provided the products are installed before the expiration of the shelf life). THERE ARE NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR THE PURPOSE FOR THIS PRODUCT WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. ATLAS' LIABILITY FOR ALLEGED BREACH OF THIS WARRANTY SHALL BE LIMITED TO REPAIR OR REPLACEMENT OF THE DEFECTIVE PRODUCT (BUT NOT INCLUDING REMOVAL OF THE DEFECTIVE PRODUCT OR INSTALLATION OF REPLACEMENT PRODUCTS). ATLAS SHALL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES DURING THE WARRANTY PERIOD OR THEREAFTER. **ATLAS' WARRANTY IS VOIDED IF PAYMENT FOR PRODUCT IS NOT RECEIVED IN FULL**.

**Note:** Atlas makes it a practice to continuously update and enhance our Asphalt products. This may result in slight discrepancies between our printed Data Sheets and the current version. For the most recent version of any Data Sheet, please visit our Web site at www.atlasmin.com